

Expanded Polystyrene Insulation.

R-Shield® expanded polystyrene insulation is a cost effective, durable, and energy efficient solution for all types of insulation applications. R-Shield Insulation is an insulation manufactured to provide architects, specifiers, distributors, and contractors all the features and benefits inherent in a quality insulation.

R-value – R-Shield 250 has an R-value that never changes over time.

Strength – R-Shield 250 has a compressive strength of 25 psi.

Moisture Resistance – R-Shield 250 is a closed cell polystyrene insulation and is resistant to moisture gain.

Vapor Permeable – R-Shield 250 allows moisture vapor to move through its structure.

Drying Potential – R-Shield 250 rapidly releases absorbed moisture.

Applications.

- Cavity Wall
- Wall Sheathing
- Precast Concrete Core
- Flat/Tapered Roofing
- Plaza Deck/Vegetative Green Roof
- Perimeter/Underslab
- Drainage Board
- Waterproofing Protection


Proven to meet, or exceed, building codes.

R-Shield insulation is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER40361-01 and ICC ESR-4743.



R-Shield insulation meets Type IX of ASTM C578, “Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation”.



		
Compressive Strength ^{1,2} @ 10% deformation, min. ASTM D1621	psi (kPa)	25 (173)
R-value ¹ , Thermal Resistance, per inch, ASTM C518	25°F	°F·ft ² ·h/Btu (°K·m ² /W) 5.0 (0.88)
	40°F	°F·ft ² ·h/Btu (°K·m ² /W) 4.8 (0.85)
	75°F	°F·ft ² ·h/Btu (°K·m ² /W) 4.4 (0.77)
k-value Thermal Conductivity ASTM C518	25°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.20 (0.029)
	40°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.21 (0.030)
	75°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.23 (0.033)
Density, Nominal ASTM C303	lb/ft ³ (kg/m ³)	2.0 (32)
Flexural Strength ¹ , min. ASTM C203	psi (kPa)	50 (345)
Water Vapor Permeance ¹ of 1.0 in. thickness, max., perm ASTM E96		2.5
Water Absorption ³ , volume % ASTM C272		0.3
Flame Spread Index ASTM E84		<25
Smoke Developed Index ASTM E84		<450
Maximum long-term use temperature		165°F (74°C)
ASTM C578 Compliance, Type		IX

¹ Please refer to ASTM C578 specification for complete information.

² Compressive strength is measured at 10 percent in accordance with ASTM C578. A safety factor is required to prevent long-term creep for sustained loads. For static loads, a safety factor of 3:1 is recommended.

³ ASTM C272 24 hour immersion followed by 24 hour storage in 75°F/50%RH air.

Thermal Performance.

The R-value of R-Shield insulation remains constant and does not suffer from R-value loss. The closed cell structure of R-Shield insulation contains air and not blowing agents which deplete over time.

Exposure to Water and Water Vapor.

The mechanical properties of expanded polystyrene are unaffected by moisture. Exposure to water or water vapor does not cause swelling.

Temperature Exposure/Flame Retardants.

Expanded polystyrene is able to withstand the rigors of temperature cycling, assuring long-term performance.

Although flame retardants used in the manufacture of expanded polystyrene provide an important margin of safety, all expanded polystyrene products must be considered combustible.

The maximum recommended long-term exposure temperature for R-Shield insulation is 165°F (74°C).

Weathering.

Long-term exposure to sunlight causes yellowing and a slight embrittlement of the surface due to ultraviolet light. This has little effect on mechanical properties. If stored outdoors, cover expanded polystyrene with opaque polyethylene film, tarps, or similar material.

Termite Resistant.

Foam plastic insulations have been shown to become termite infested under certain exposure conditions. R-Shield insulation is resistant to termite infestation. Please review literature on R-Shield insulation with termite resistance for complete information.

Resistance to Mold and Mildew.

Expanded polystyrene will not decompose and will not support mold or mildew growth. Expanded polystyrene provides no nutrient value to plants or animals.

Adhesives, Coatings, and Chemicals.

Solvents which attack expanded polystyrene include esters, ketones, ethers, aromatic, and aliphatic hydrocarbons and their emulsions, among others. If expanded polystyrene is to be placed in contact with materials (or their vapors) of unknown composition, pretest for compatibility at maximum exposure temperature.

Do not install or use expanded polystyrene with coal tar pitch, highly solvent-extended mastics, or solvent-based adhesives without adequate separation.

Warranty.

Premier Building Systems offers a product warranty ensuring thermal performance, physical properties, and termite resistance.

A PRODUCT OF
PREMIER
BUILDING SYSTEMS



www.rshieldinsulation.com | 800-766-3626

Copyright © 2022. R-Shield is a registered trademark of Premier Building Systems. RSI 02 08/22